soudokay

SK 410 NiMo-O

DIN 8555: MF 5-GF-40

I DESCRIPTION

1

Alloy depositing a ferritic-martensitic steel containing 13% Chromium, 5% Nickel and 1% Molybdenum designed to resist metal-to-metal wear, corrosion and thermal fatigue fire cracking.

I SUITABLE FOR

2

Continuous casting rollers.

I TYPICAL CHEMICAL ANALYSIS (WEIGHT %)

3

	С	Mn	Si	Cr	Ni	Мо	Fe
All Weld	0.05	0.4	0.2	12.50	4.50	0.5	Bal.

I TYPICAL MECHANICAL PROPERTIES

4


Hardness as welded

40 HRC

I GENERAL CHARACTERISTICS

E

- Microstructure Martensite + 10% Ferrite
 Machinability Good with carbide tipped tools
- Oxy-acetylene cutting
 Cannot be flame cut
- Deposit thickness
 Depends upon application and procedure used
- Flux cored



WELDING PARAMETERS & ECONOMICAL DATA

6

The information about the products contained in the data sheets are based on intensive tests and careful investigations. However we can't assume any form of liability concerning the exactness of it. The information may be changed or updated without previous notice. The user is invited to test the product with regard to his own application and responsibility.



| SOUDOKAY SA | RUE DE L'YSER 2 | B-7180 SENEFFE | BELGIUM | soudokay @soudokay.be | www. soudokay.com | SALES: T +32 (0)64 51 02 25 | LOGISTICS: T +32 (0)64 51 02 10 | FINANCE: T +32 (0)64 52 00 30 | F +32 (0)64 51 02 21 | F +32 (0)64 51 02 19 | F +32 (0)64 52 00 31